

SEABOARD ASPHALT COMPANY PROFILE

Seaboard Asphalt Products Company is a privately owned company located in Baltimore, Maryland USA since 1929. Seaboard manufactures a over 600 products manufactured with our asphalt emulsion, coal tar emulsion and asphalt cutbacks. Some of these products include roof coatings, waterproof coatings, air barriers, driveway sealers, crackfillers, tack coats, aluminum coatings, white elastomeric coatings, tennis court coatings, cold mix asphalt and binders and a wide variety of specialty coatings. Seaboard is also one of largest packagers of ice melt in bags in the mid-Atlantic area. Seaboard currently produces over 250 private label brands of these coatings. Seaboard distributes product to all 50 U.S. States and over 50 Foreign Countries.

The owners of Seaboard acquired Specialty Emulsions in 2004 (Specialty Emulsions had been operating as Koch Materials for 40 years). Specialty Emulsions manufactures a variety of specialty and road paving grade asphalt emulsions in York, Pennsylvania USA.

The manufacturing assets of these companies allows us to provide all grades of asphalt emulsions, coal tar emulsions and asphalt cutbacks and formulate specialty grades of these for our customers. Seaboard and Specialty can also provide all packaging needs from bulk, totes, drums, pails, gallons, quarts and pints.

Additional information can be found on our websites at www.seaboardasphalt.com and www.specialtyemulsionsinc.com or contact our offices at 410-355-0330 or your local representative.

SEABOARD ASPHALT PRODUCTS COMPANY

PRODUCT DATA EMULSION COATING

EM-13 POLYMER MODIFIED ASPHALT EMULSION COATING

PRODUCT DESCRIPTION:	Clippership EM-13 is a single component non-flammable polymer modified asphalt emulsion coating.	
BASIC USES:	Clippership EM-13 is a spray, brush, or roll coating designed to protect from corrosion, waterproofing, environmental elements and achieves excellent durability, flexibility, and is quick drying.	
LIMITATIONS:	DO NOT ALLOW material to freeze. DO NOT THIN material.	
APPLICATION:	Clippership EM-13 must be applied to a surface that is free from all foreign matter. This material should remain dry until it has cured. This material should be mixed before using and yields a coverage of 250-350 square feet per gallon.	
STORAGE:	Clippership EM-13 must be kept from freezing.	
MATERIAL SPECIFICATIONS:	Weight per Gallon @ 77°F, ASTM-D-1010, (lbs)	8.3-8.7
	Nonvolatile %, ASTM-D-2939	55.0-64.0
	Viscosity @ 77°F, ASTM-D-562 (Kreb's Stormer Unit)	45-65 KU
	Softening Point (0°F), ASTM-D-36	170-180
	Penetration (0.1 mm), ASTM-D-5	20-40
	Std. Spec. for Emulsified Asphalt	
	AASHTO Designation M140-70	meets spec.
	ASTM Designation D997-73	meets spec.
	Resistance to water, ASTM-D-2939	no blistering, no loss of adhesion, no re-emulsification
	Dry Time (hrs.) ASTM-D-2939	less than 1
	Shelf Life (yrs.)	1-2

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from law or patent implied.

3601 FAIRFIELD ROAD
BALTIMORE, MARYLAND 21226
(410) 355-0330
(800) 536-0332
FACSIMILE (410) 355-5864

SEABOARD ASPHALT PRODUCTS COMPANY

PRODUCT DATA ASPHALT PAINT

LN-12 QUICK DRYING ASPHALT GILSONITE PAINT

PRODUCT DESCRIPTION:	Seaboard Gilsonite Paint is a superior quick drying asphalt paint formulated to meet Federal Specification TTC-494 Types I, II, and III.	
BASIC USES:	Seaboard Gilsonite Paint is used as a tough and weather resistant coating on all types of steel, piping, industrial equipment chassis, radiators, burial vaults, concrete precast, septic tanks, and concrete manholes, etc.	
LIMITATIONS:	DO NOT HEAT container.	
APPLICATION:	Seaboard Gilsonite Paint may be brushed or sprayed onto a clean and dry surface. This material dries in one hour and cures in approximately five hours.	
STORAGE:	Seaboard Gilsonite Paint should be kept in a warm area before usage during cold seasons, but this material can be used year round and the only protection would be from weathering on the container.	
COMPOSITION:	Asphalt	CAS 8052-42-4
	Solvent	CAS 64741-41-9
	Gilsonite	CAS 12002-43-6

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from law or patent implied.

3601 FAIRFIELD ROAD
BALTIMORE, MARYLAND 21226
(410) 355-0330
(800) 536-0332
FACSIMILE (410) 355-5864

SEABOARD ASPHALT PRODUCTS COMPANY

PRODUCT DATA JOINT COMPOUND

MP-52 BITUMINOUS JOINT COMPOUND

PRODUCT DESCRIPTION:	Seaboard Bituminous Joint Compound is a trowel mastic asphaltic compound for joint sealing and is 100% ASBESTOS-FREE. MP-52 is manufactured to meet the requirements for ASTM-D-2822 and ASTM-D-4586 Type I.	
BASIC USES:	Seaboard Bituminous Joint Compound is used as a joint sealant for concrete pipe, foundations, and all other masonry and steel joint sealing.	
LIMITATIONS:	DO NOT HEAT container.	
APPLICATION:	Seaboard Bituminous Joint Compound can be applied by trowel in a liberal fashion to fill the joint completely.	
STORAGE:	Seaboard Bituminous Joint Compound can be used year round and the only protection would be from weathering on the container.	
COMPOSITION:	Asphalt	CAS 8052-42-4
	Mineral Spirits	CAS 64741-41-9
	Fibre	CAS 65996-61-4
		CAS 9004-34-6
	Amine Salt	CAS 30113-45-2
	Clay	CAS 8031-18-3

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from law or patent implied.

3601 FAIRFIELD ROAD
BALTIMORE, MARYLAND 21226
(410) 355-0330
(800) 536-0332
FACSIMILE (410) 355-5864